

# Technical Specification

MARCHÉ on Eco-Tile™

*Specification Sheet: Marché Field Tile*

*Testing Data: Field Tile Specifications as related to ANSI A137.1 Table 8*

**Marché on ECO-TILE - Snow White Crackle**

*Not recommended for (steam) shower wall installations*

**Seal Snow White Crackle with penetrating sealer before grouting**

**Marché on ECO-TILE:**

**Product is “Pressed Floor and Wall”, “Natural”, Class P4,**

**Recommended Grout Joint: 3/16” minimum**

**Variation from average sample facial dimension:  $\pm .75\%$  or  $.09$ ”, whichever is less**

**Nominal Size:  $\pm 4\%$  from sample**

**Modularity: None**

**Warpage Edge: Max / Min range  $\pm 1\%$  or  $.012$ ”, whichever is less**

**Warpage Diagonal: Max / Min range  $\pm .75\%$  or  $.13$ ”, whichever is less**

**Wedging: Max / Min range  $\pm 1\%$  or  $.12$ ”, whichever is less**

**Thickness: 3/8” Range- maximum of  $+ .040$ ”**

**Absorption: 7%-20%**

**Color Uniformity: V2 – V3 Slight to Moderate variation dependent on color choice**

**Crazing Resistant: Pass except on crackle glazes, Crackle glazes must be sealed prior to grouting.**

**Breaking Strength: Avg. 250lbf individual 225 lbf. Standard wall tile is 100 lbf-125 lbf.**

**Freeze / Thaw: Not suitable for exterior installation in freeze thaw climates**

**Setting and Grouting Materials: Latex Portland cement, Mastic, or Epoxy. Care should be taken in grout color selection as tile surface will grout grab and may be very difficult to clean thoroughly**

*You may want to seal tile before using contrasting grout.*

**Cleaning: Accomplished with PH neutral soap and water**

Quarry Tile Co., 6328 East Utah Ave, Spokane, WA 99212 | ph: 800.423.2608 | fx: 509.536.4072